

ITEM 580.51030525 - FULL DEPTH REMOVAL OF STRUCTURAL SLAB AND REPLACEMENT WITH CLASS D CONCRETE

1. DESCRIPTION:

- 1.01 The work shall consist of the full depth removal and disposal of unsound concrete from the existing structural slab and its replacement with Portland Cement Concrete, Class D, as indicated on the contract plans or where ordered by the Engineer.
- 1.02 Materials removed as part of this work shall be transported from the work site and disposed of by the Contractor, unless otherwise indicated on the contract plans, or ordered by the Engineer.

2. MATERIALS:

- 2.01 All the provisions of Subsection 555-2 Materials shall apply.
- 2.02 The gradation requirement for the mixture shall be as indicated in Table 501-2, Coarse Aggregate Gradations.

3. CONSTRUCTION DETAILS:

- 3.01 The provisions of Subsection 555-3 Construction Details shall apply.
- 3.02 Before starting work on this item, the Contractor shall submit to the Engineer for approval, a plan showing his proposed method, equipment and sequence for the removal work. No blasting or dynamiting will be permitted. The requirements of §580-3 of the Standard Specifications shall apply. The Contractor shall provide adequate protection, approved by the Engineer, at the bridge site to completely preclude any possibility of material dropping from the bridge onto highways, residences, railroads, rivers or any other objects below.
- 3.03 **Repair Determinations:** All repair locations will be determined by the Engineer prior to commencement of the removals. The Engineer shall be allotted one working day per span or portion thereof being worked on for his inspection. The Engineer shall sound the area to be repaired by examining the top and bottom of the deck visually and then by chain drag. Areas then determined to be unsound, shall be clearly marked.
- 3.04 **Removal of Unsound Concrete:** The existing concrete shall be sawcut to a minimum depth of 1 inch, unless otherwise noted on the contract plans, to obtain a straight (keyed) joint between the existing concrete and the new material. Special care shall be taken to insure that reinforcing steel to remain is not damaged by the saw blade. All unsound concrete shall be removed to a 6 on 1 sloped sound surface as determined by the Engineer. Care shall be taken while removing the unsound concrete so as not to damage materials that are to remain in place such as reinforcing steel and shear connectors. Material which is damaged shall be repaired or replaced in a manner satisfactory to the Engineer at the expense of the Contractor. Exposed reinforcement remaining in place shall be cleaned in accordance with the requirements of Subsection 556-3.01 of the Standard Specifications. Exposed shear connectors that remain in place shall be cleaned in a manner satisfactory to the Engineer. Upon completion of unsound concrete removal, the sound concrete surfaces shall be air-blown or vacuum cleaned. Air-blowing may be used on vertical or overhead surfaces. Vacuum cleaning will be required for all other surfaces.

ITEM 580.51030525 - FULL DEPTH REMOVAL OF STRUCTURAL SLAB AND REPLACEMENT WITH CLASS D CONCRETE

3. CONSTRUCTION DETAILS: (cont'd)

3.04 (cont'd)

For any structural concrete removal item, where a hammer size limitation is specified on the plans or in the specification, the Engineer may order the Contractor to use a lighter hammer than that specified, if, in his opinion, the hammer being used is destroying concrete that should remain. A hammer heavier than that specified may be used if written permission is secured from the Engineer.

Existing reinforcing shall not be removed unless otherwise indicated in the plans or proposal, or as directed by the Engineer. Replacement reinforcement shall be as ordered by the Engineer and be of like size and galvanized.

3.05 **Preparation & Placement:** Immediately prior to the placement of new concrete, existing concrete surfaces shall be abraded, cleaned and made saturated surface dry as per the Contract Plans.

3.06 **Curing:** Apply an approved spray curing compound, immediately after the concrete placement. The remaining curing procedure shall be in conformance with the Standard Specifications.

4. METHOD OF MEASUREMENT:

4.01 Measurement shall be made as the number of square feet of structural slab replaced. No additional measure shall be included for haunch areas or other areas of greater than average thickness.

5. BASIS OF PAYMENT:

5.01 The unit price bid per square foot shall include the cost of furnishing all labor, materials, and equipment, necessary to satisfactorily complete the work.

5.02 Replacement of deteriorated reinforcement shall be paid for under its appropriate pay item as shown on the plans. Reinforcement requiring replacement due to damage from the Contractor's operations shall be replaced at no cost to the Authority.